

TEST REPORT

Page 1 of 7

REPORT NUMBER : TURT250000142
APPLICANT NAME ASD Laminat A.Ş.
ADDRESS Organize Sanayi Bölgesi 81600 Beyköy Bakırköy / Düzce
Tel: 0380 553 72 01
Attention : İsmail Altındal (ismaila@asdlaminat.com)
SAMPLE DESCRIPTION : One sample of White wood panel (LABCO)
DATE IN : 02 January, 2025 (09:09)
DATE OUT : 17 January, 2025

TEST	Sample
CHEMICAL STAIN RESISTANCE (±)	NR

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES /
X=NOT PERFORMED / #.SEE RESULT

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party, nor could it be used for PR activities. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered.



İrem YURTVERMEZ YILMAZ
Customer Care Executive



Emre ÇALIK
Chemical Laboratory Manager

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altındag Plaza Yenibosna 34197 - ISTANBUL / TURKEY
Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55
e-mail : intertekcg.turkiye@intertek.com
www.intertek-turkey.com



250000142

CHEMICAL STAIN RESISTANCE (‡)

SECTION 1

CONCLUSION

TEST	RESULTS
2.1 - Chemical Stain Resistance	Conforming*

* Suitability for a given application is dependent upon the chemicals used in a given laboratory.

SAMPLE DISPOSITION

All samples remain at Intertek at the issuance of this report.

SUBMITTED TEST SAMPLE



Figure 1: Sample as received

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com

SECTION 2

2.1 - CHEMICAL STAIN RESISTANCE:

Date Received: 09-January-2025
 Date Tested: 13-January-2025 to 14-January-2025
 Location Tested: Intertek Kentwood, MI

DESCRIPTION OF SAMPLES:

Part Description: White Panel (Labco) (TURT250000142)
 Material Specification: SEFA 3 – 2020: Section 2.1
 Condition of Samples: Production

TEST PROCEDURE:

Test Method: SEFA 3 – 2020: Section 2.1
 Number of Samples: One (1)

ACCEPTANCE CRITERIA:

Per SEFA 3 – 2020: Section 2.1

The Range of Results is provided to establish the acceptable range for Laboratory Grade Finish. Results will vary from manufacturer to manufacturer. Laboratory grade finishes should result in no more than four (4) Level 3 conditions. Suitability for a given application is dependent upon the chemicals used in a given laboratory.

RESULTS:

See Tables 1-2 and Figures 2-3.

Table 1. 8.1 Chemical Spot Test Results

TEST NO.	CHEMICAL (% BY VOL.)	METHOD	RATING	COMMENTS
1	Acetate, Amyl	A	0	N/A
2	Acetate, Ethyl	A	0	N/A
3	Acetic Acid, 98%	B	0	N/A
4	Acetone	A	0	N/A
5	Acid Dichromate, 5%	B	0	N/A
6	Alcohol, Butyl	A	0	N/A
7	Alcohol, Ethyl**	A	0	N/A
8	Alcohol, Methyl	A	0	N/A
9	Ammonium Hydroxide, 28%	B	0	N/A
10	Benzene	A	0	N/A
11	Carbon Tetrachloride	A	0	N/A
12	Chloroform	A	0	N/A
13	Chromic Acid, 60%	B	0	N/A

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com

RESULTS

Page 4 of 7

REPORT: TURT250000142

17 January, 2025

TEST NO.	CHEMICAL (% BY VOL.)	METHOD	RATING	COMMENTS
14	Cresol	A	0	N/A
15	Dichloroacetic Acid	A	0	N/A
16	Dimethylformamide	A	0	N/A
17	Dioxane	A	0	N/A
18	Ethyl Ether	A	0	N/A
19	Formaldehyde, 37%	A	0	N/A
20	Formic Acid, 90%	B	0	N/A
21	Furfural	A	0	N/A
22	Gasoline	A	0	N/A
23	Hydrochloric Acid, 37%	B	0	N/A
24	Hydrofluoric Acid, 48%	B	1	Change in gloss
25	Hydrogen Peroxide, 30%	B	1	Change in gloss
26	Iodine, Tincture of	B	1	Change in color
27	Methyl Ethyl Ketone	A	0	N/A
28	Methylene Chloride	A	0	N/A
29	Monochlorobenzene	A	0	N/A
30	Naphthalene	A	0	N/A
31	Nitric Acid, 20%	B	1	Change in color
32	Nitric Acid, 30%	B	1	Change in color
33	Nitric Acid, 70%	B	1	Change in color
34	Phenol, 90%	A	0	N/A
35	Phosphoric Acid, 85%	B	1	Change in color
36	Silver Nitrate, Saturated	B	0	N/A
37	Sodium Hydroxide, 10%	B	1	Slight change in color/ gloss
38	Sodium Hydroxide, 20%	B	1	Change in gloss
39	Sodium Hydroxide, 40%	B	0	N/A
40	Sodium Hydroxide, Flake	B	0	N/A
41	Sodium Sulfide, Saturated	B	0	N/A
42	Sulfuric Acid, 33%	B	0	N/A
43	Sulfuric Acid 77%	B	0	N/A
44	Sulfuric Acid, 96%	B	1	Change in color
45	Sulfuric Acid, (77%) and Nitric Acid (70%), equal parts	B	1	Change in color
46	Toluene	A	0	N/A
47	Trichloroethylene	A	0	N/A
48	Xylene	A	0	N/A
49	Zinc Chloride, Saturated	B	0	N/A

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com
www.intertek-turkey.com

RESULTS

Page 5 of 7

REPORT: TURT250000142

17 January, 2025

***If the use of this chemical is permitted by law, in the country where this testing is being performed.**

****Black smudge from chemical reacting with sharpie label.**

Table 2. 8.1 Chemical Spot Test Results

TOTAL			
ITEMS	REQUIREMENT	NO. REAGENTS WITH 3 RATINGS	DISPOSITION
Volatile Subtotal	-	0	-
Non-volatile Subtotal	-	0	-
Grand Total	No more than four Level 3 conditions	0	*Conforming

* Suitability for a given application is dependent upon the chemicals used in a given laboratory

PHOTOGRAPHS




Figure 2: Test set up

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com




Figure 3: Results

(‡) The test was performed by an approved subcontractor laboratory which is part of the Intertek Group.

SAMPLE PHOTO



END OF TEST REPORT